


# TECHNICAL DATA SHEET (TDS)

## ONGRONAT® TR 5050



- **Product Description:** ONGRONAT® TR 5050 is a mixture of monomeric MDI isomers, polymeric MDI and polyether based prepolymer
- **Appearance:** Solvent free dark-brown low viscosity liquid at room temperature
- **Industry:** Transport
- **Applications:** ONGRONAT® TR 5050 can be used as isocyanate component for the manufacture of flexible moulded foam for automotive applications. The product is particularly suitable for the production of seat cushions.

### SPECIFICATIONS

Property	Value	Dimension	Test Method
NCO	28.4 - 30.4	wt%	BorsodChem Method PAK 155
Viscosity [at 25 °C]	40 - 110	mPa.s	ASTM D4889

### OTHER PROPERTIES\*

Property	Value	Dimension
Density [at 25 °C]	1.19	g/cm <sup>3</sup>
Flash point	>200	°C

\*Parameters given in the other property range are only typical values; therefore they are not part of the specification.

### PACKING, STORAGE & TRANSPORT

Transport and packing: ONGRONAT® TR 5050 can be transported in road tankers, 1000 l containers (IBCs), 250 kg non-returnable metal drums, or in metal cans under nitrogen blanket. ONGRONAT® TR 5050 is loaded in the temperature range of 40 – 45 °C. Please note that based on the distance of the destination the delivery temperature may differ from the loading temperature, but still remains in the range of 20 – 45 °C delivering the product in bulk. In case of shipping by normal truck (in drums or IBCs) the delivery temperature can not be warranted. Transporting ONGRONAT® TR 5050 by the means of thermo trucks in drums or IBCs the temperature must be kept in the range of 20 – 30 °C.


Storage: It is recommended to store ONGRONAT® TR 5050 within the temperature range of 20 – 30 °C. Under these conditions the product preserves its quality for max. six (6) months from the date of its production. The material can also be stored within the temperature range of 15-30 °C without affecting its quality significantly. During storage below 15 °C the quality of ONGRONAT® TR 5050 can deteriorate because of the partial crystallisation of its 4,4'-methylene diphenyl diisocyanate content. The product can be liquefied again by heating it up to 70°C as rapidly as possible in a controlled way. During this re-melting procedure sediment can be generated.

If the product is not consumed immediately after re-melting, it is necessary to ensure storage at the recommended temperature. Storage at a temperature above 30 °C is not recommended since discolouration and formation of insoluble solids (dimerization) may occur, which can lead to a viscosity increase and a decrease of NCO content. Above 150 °C a slow, exothermic decomposition reaction takes place that becomes extremely fast above 250 °C, so care must be taken to avoid this effect.

The material must be kept dry at all times; it must be protected from water ingress and atmospheric moisture. In order to protect the material from atmospheric moisture a dry inert gas blanket (nitrogen) with a dew point of -40 °C must be used for any type of containers (drums or storage tanks). Dry air is not recommended for this purpose because it may cause oxidation and due to this, the colour of the product can become darker. Since carbon dioxide (CO<sub>2</sub>) is soluble in isocyanates it is not recommended to use as an inert gas either.

# TECHNICAL DATA SHEET (TDS)

## ONGRONAT® TR 5050



### SAFETY PRECAUTIONS

All activities related to isocyanate handling are potential sources of danger; therefore special care must be taken when

working with it. Handle the material with care. Avoid contact with water and moisture. Avoid contact with skin and eyes. Do not inhale the vapours of the product. Detailed safety information available in the specific Safety Data Sheet.

Version: English  
Date: 01.10.2019  
Technical Data Sheet (TDS)  
ONGRONAT TR 5050

---

[www.borsodchem-group.com](http://www.borsodchem-group.com)

This information is based on our most recent knowledge. However, the application and processing of the material after sale is beyond our control and we cannot assume responsibility for use of this material outside BorsodChem premises. The user is obliged to check the suitability of this material for the intended use and accepts sole responsibility for compliance with any legal requirements relating to its use. This document does not constitute a warranty or guarantee.



**Manufactured by:**

**BorsodChem Zrt.**  
Bolyai tér 1  
H-3700, Kazincbarcika  
HUNGARY  
Phone: +36-48-511-211  
Fax: +36-48-511-511